



Mineral Services: (203) 4810646 – 4810502 - 4810190
Alexandria Port Office: Gate 14, VIP Building 2nd Floor
Head Office : (202) 29179506
E-mail : sgs_egypt@sgs.com
Our Ref. No. : MIN11-1379
Date : 18th July 2011
Issuance : Alexandria
Certificate No.: F190201/Ore001354

QUALITY CERTIFICATE

According to instructions received from Messer's "TAS FLOWRANCE Export & Import", to perform sampling, identified as indicative samples, and analysis for a shipment designated as per a client's statement emailed to us showing the following :-

Cargo : SILICA SAND
Quantity : About 6000 TONS
Place of Inspection : CLIENT'S STORES AT PORT SAID EAST

WE CERTIFY THAT:

Sampling:-

Carried out by our inspector on 13th July 2011 at client's stores at port said east, from reasonable number of Jumbo Bags according to BS 2975/2004, forming an indicative sample which duly and thoroughly mixed then divided into three indicative sub-samples Which labeled and sealed then distributed as follows:-

- **Two** Sealed and labeled samples with SGS Seals Nos. I2235178 and I2235179 retained by us, for a period of three months from sampling date unless written instructions received.
- **One** Sealed and labeled sample with SGS Seal No. I2235180 for analysis purposes.

Analysis:-

According to analysis carried out at SGS Mineral Laboratory, for indicative sample drawn by us on 13th July 2011 with SGS seal No. I2235180, where the analysis results were as follow:-

Chemical Analysis:-

Test	Results %	Ref. Method
Moisture	0.04	BS 2975:1988
L.O.I	0.14	
SiO ₂	99.67	AAS
Fe ₂ O ₃	0.012	
Al ₂ O ₃	0.11	
TiO ₂	0.017	
CaO	0.02	
MgO	0.003	
Na ₂ O	0.005	
Sieve analysis		BS 2975:1988
+ 0.600	1.93	
+0.425 -0.600	8.88	
+0.250- 0.425	40.22	
+0.125 – 0.250	47.17	
-0.125	1.80	

Due to the inaccessibility of part of the cargo, the samples collected have indicative value only and will not necessarily be representative of the entire cargo, but only of that part accessible and sampled at the date, time, and place of inspection. Sampling from any stationary stockpile is considered to be non-truly representative for the obvious reasons: the material is in static condition, not in movement and all the inner layers of material inside the pile are not accessible during sampling from the stockpile.

Sampling will be carried out manually at depth 40cm from the pile's surface. Samplings from stockpiles are always limited.

As a stationary stockpile limited sampling may not be truly representative of the entire cargo lot, the results of analysis may reflect the quality of the collected samples only. Therefore the stockpile pre-loading inspection findings may be used for the indicative / informative or estimation Purposes only prior to loading and none can be used for any kind of commercial final purposes or transactions.

End of Certificate



This document is issued by the Company under its General Conditions of Service printed overleaf. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGSPAPER
11058095

